# Product data sheet Triflex Manhole Frame Filler

#### Use

Heavy duty, rigid screed and repair material.

### **Properties**

- Cold liquid applied
- Exceptionally fast curing
- Semi-flexible
- Chemical resistant
- UV resistant
- Mechanically resistant
- Solvent and isocyanate free

## Components

| Component | Product  | Ratio              |
|-----------|--|--------------------|
| Resin     | Triflex<br>Schachtrahmenverguss R                        | 2.8 parts (2.80Kg) |
| Filler    | Triflex<br>Schachtrahmenverguss S<br>(includes catalyst) | 25 parts (25.00Kg) |

| Packaging |                |             |
|-----------|----------------|-------------|
| Component | Pack size      |             |
| Resin     | Drum:          | 25.00Kg     |
| Filler    | Bag:           | 20.00Kg     |
|           | Multiply bags: | 9 x 25.00Kg |

# Colour(s)

• Buff

# **Application conditions**

| Condition                         | Value               |
|-----------------------------------|---------------------|
| Ambient and substrate temperature | 0°C to +35°C        |
| Relative atmospheric<br>humidity  | Up to 95%           |
| Dew point                         | 3°C above dew point |

## Substrate assessment / pretreatment / preparation

Ensure that the substrate is clean, dry and free from dust, laitance, grease, oil and any other contaminants and assess / pre-treat / prepare substrate in accordance with Triflex Specification proposal.

## Initial resin mixing / decanting

- Thoroughly mix the resin in the drum with a slow speed mixer until the resin achieves a uniform consistency;
- 2. Decant 2.80Kg (2.90Litres) per 25.00Kg bag of filler.



# Mixing

- Add the filler to the pre-mixed / decanted resin in the ratio 4 parts filler to 1 part resin (by weight) by slowly pouring the filler into resin and thoroughly mixing with a slow speed mixer until the mixture achieves a smooth, uniform consistency and colour;
- 2. Use the mixed material within the pot life.

# **Application method**

Trowel or tamp. Ensure that the material is very well compacted.

## Pot life (at 20°C)

Approximately 15 minutes.

Note: Times will be slightly increased at lower temperatures and slightly reduced at higher temperatures.

## Density

1.90Kg/mm/m<sup>2</sup>

| Curing time                        |                          |  |
|------------------------------------|--------------------------|--|
| Condition                          | Time                     |  |
| Rainproof                          | Approximately 30 minutes |  |
| Can be walked on / over-<br>coated | Approximately 45 minutes |  |
| Able to withstand stress           | Approximately 1 hours    |  |

Note: Times will be slightly increased at lower temperatures and slightly reduced at higher temperatures.

#### Interruptions during works

Unless the surface is fully aggregate filled, if work is interrupted for more than 12 hours or if soiled by rain etc., use Triflex Cleaner to clean and reactivate the transition area. Overlay after Triflex Cleaner has evaporated and a minimum 20 minutes / maximum 60 minutes after application. If the surface is aggregate filled ensure that the surface is clean, dry and free from dust, grease, oil and any other contaminants prior to overlay but do not apply Triflex Cleaner.

## **Tool cleaning**

Clean tools with Triflex Cleaner.



## Storage / shelf life

Store unopened in a cool, dry, well ventilated place above freezing, out of direct sunlight and in the original container.

Shelf life if stored correctly: minimum 6 months / maximum 12 months.

## Health and safety

Refer to Safety Data Sheets.

#### **Disposal information**

Refer to Safety Data Sheets for recommended EWC waste codes.

#### Notes

The advice we provide on the application of our products is based on extensive development work and many years of experience, and is given to the best of our knowledge. The wide variety of requirements for a building under the most diverse conditions mean that it is necessary for the contractor to test the product for suitability in each case. Triflex reserve the right too make alterations in keeping with technical developments or improvements.

Non-Triflex products must not be used with Triflex systems.

Only the most recent version of this data sheet is valid.